

# SKW Associates, Inc.

3370 Victor Court

Santa Clara, CA 95054

Phone (408) 919-0094

Fax (408) 919-0097



Email: [skw@testwafer.com](mailto:skw@testwafer.com)

<http://www.testwafer.com>

# SKW 6-6 Cu/BD/TEOS V1.0

## Wafer Specifications

DATE: August 3, 2006



Cross Sectional View

SKW 6-6 Cu/BD/TEOS Mask Floor Plan

PARAMETER	NOMINAL	TOLERANCE
Patterning		
Center Die X Location	-14.01 mm	+/- 100 μm
Center Die Y Location	-12.41 mm	+/- 100 μm
Die Size: X	25 mm	+/- 10 μm
Die Size: Y	32 mm	+/- 10 μm
Die Stepping (X / Y)	244 / 210 μm	+/- 10%

Wafers must be patterned all the way to the edges of the wafer, i.e. no area anywhere on the wafer unpatterned. (Under certain stepper operating conditions, 2 mm edge edge exclusion is allowed.)

PARAMETER	NOMINAL	TOLERANCE
Line CD Variation (measured on 2 $\mu\text{m}$ structure)		
Lot-to-Lot	2 $\mu\text{m}$	+/- 10 nm
Within-Lot (Wafer-to-Wafer)		+/- 10 nm
Within-Wafer		+/- 10 nm
Within-Die (measured on 9 trenches)		+/- 10 nm
Pad Oxide thickness		
Lot-to-Lot	200 $\text{\AA}$	+/- 5 %
Within-Lot (Wafer-to-Wafer)		+/- 5 %
Within-Wafer		+/- 3 %
Within-Die		+/- 3 %
SiN film thickness		
Lot-to-Lot	1650 $\text{\AA}$	+/- 10 %
Within-Lot (Wafer-to-Wafer)		+/- 10 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %
Black Diamond film thickness		
Lot-to-Lot	2600 $\text{\AA}$	+/- 8 %
Within-Lot (Wafer-to-Wafer)		+/- 8 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %
TEOS Oxide thickness		
Lot-to-Lot	600 $\text{\AA}$	+/- 10 %
Within-Lot (Wafer-to-Wafer)		+/- 10 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %

<b>PARAMETER</b>	<b>NOMINAL</b>	<b>TOLERANCE</b>
PVD Ta film thickness		
Lot-to-Lot	60 Å	+/- 10 %
Within-Lot (Wafer-to-Wafer)		+/- 10 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %
PVD TaN film thickness		
Lot-to-Lot	90 Å	+/- 10 %
Within-Lot (Wafer-to-Wafer)		+/- 10 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %
PVD Cu film thickness		
Lot-to-Lot	800 Å	+/- 10 %
Within-Lot (Wafer-to-Wafer)		+/- 10 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %
ECD Cu film thickness		
Lot-to-Lot	5700 Å	+/- 10 %
Within-Lot (Wafer-to-Wafer)		+/- 10 %
Within-Wafer		+/- 5 %
Within-Die		+/- 5 %